



# LOCTITE<sup>®</sup> 8014<sup>™</sup>

December 2009

## PRODUCT DESCRIPTION

LOCTITE<sup>®</sup> 8014<sup>™</sup> provides the following product characteristics:

<b>Technology</b>	Anti-Seize
<b>Appearance</b>	Smooth white paste <sup>LMS</sup>
<b>Components</b>	One component - requires no mixing
<b>Cure</b>	Not applicable
<b>Application</b>	Lubrication
<b>Specific Benefit</b>	<ul style="list-style-type: none"> <li>Lubricates, seals, and prevents galling in stainless steel joints and threaded connections</li> <li>Temperature resistant to 400 °C</li> <li>Metal free formulation</li> </ul>

LOCTITE<sup>®</sup> 8014<sup>™</sup> prevents seizing, galling, friction, and wear on threaded joints and other metal-to-metal surfaces. It is a combination of white lubricating solids and extreme pressure lubricating agents in an aluminum gelled white oil. Typical applications include pipe joints, nuts, bolts and studs, flange gaskets, slip-fit, press-fit and keyed shafts, and metal-to-metal contact involving stainless steel and other stainless alloys. It is used in industrial food industries such as meat and poultry packing plants, dairy products processing plants, canning plants, grain processing plants, sugar processing plants, bakeries, beverage plants, breweries, hospitals, and other general plant maintenance. This product is typically used in applications with an operating range of -29 °C to +400 °C.

## NSF International

**Registered to NSF Category H1** for use as a lubricant with incidental food contact in and around food processing areas.

**Note:** This is a regional approval. Please contact your local Technical Service Center for more information and clarification

## TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 25 °C	1.08
Penetration, ISO 2137, unworked, 1/10 mm	340
Weight Per Gallon, lbs/gal	8.8 to 9.7 <sup>LMS</sup>
Flash Point - See MSDS	

## GENERAL INFORMATION

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a lubricant for chlorine or other strong oxidizing materials.**

**For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).**

## Directions for use:

- For best performance the mating surface should be clean and free of grease.
- Apply thin coating to threads and flats of nuts and bolts, assemble.
- Use full strength. Do not thin.

## Loctite Material Specification<sup>LMS</sup>

LMS dated October 16, 2000. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

## Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

## Conversions

(°C x 1.8) + 32 = °F
kV/mm x 25.4 = V/mil
mm / 25.4 = inches
µm / 25.4 = mil
N x 0.225 = lb
N/mm x 5.71 = lb/in
N/mm <sup>2</sup> x 145 = psi
MPa x 145 = psi
N·m x 8.851 = lb·in
N·m x 0.738 = lb·ft
N·mm x 0.142 = oz·in
mPa·s = cP

**Note**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1.2